

A193

## LIPOPHILIC INORGANIC FILLER AND COMPOSITE RESIN COMPOSITION

Patent Number: JP9087096

Publication date: 1997-03-31

Inventor(s): NAKAZAWA HIROMOTO;; YAMADA HIROHISA;; TAMURA TAKASHI;; HOSOKAWA TERUO;; INOUE HIROFUMI;; MOGI YOSHIHIRO

Applicant(s): NATL INST FOR RES IN INORG MATER;; SHOWA DENKO KK

Requested Patent: ☐ JP9087096

Application Number: JP19950248167 19950926

Priority Number (s):

IPC Classification: C30B29/34; C01B33/44; C08J5/10; C08K3/00

EC Classification:

Equivalents:

### Abstract

**PROBLEM TO BE SOLVED:** To obtain a lipophilic inorg. filler well swollen with a small amt. of org. cations and improving the heat resistance and rigidity of a composite resin compsn. having a high aspect ratio.  
**SOLUTION:** Org. cations are intercalated into a swellable silicate represented by the formula  $[A_a (X_b Y_c) (Si_4-d Al_d) O_{12} (OH)_e F_{2-e}]$  and having  $\geq 2 \mu m$  average grain diameter of single crystal grains, 70-250 Å charge density and a smectite structure to obtain the objective lipophilic inorg. filler. In the formula,  $0.2 \leq a \leq 0.7$ ,  $0 \leq b \leq 3$ ,  $0 \leq c \leq 2$ ,  $0 \leq d \leq 4$ ,  $0 \leq e \leq 2$ , A is at least one cation selected from among alkali metal ions and alkaline earth metal ions, X and Y are cations entering into each octahedron in the smectite structure, X is at least one among Mg, Fe, Mn, Ni, Zn and Li, and Y is at least one among Al, Fe, Mn and Cr.

Data supplied from the esp@cenet database - I2